

## **Technical Data Sheet**

Last revision: 28.02.2024

# griwephon sound deadening mass

#### **General Information**

Article number: AN2-750/EU

Usage: griwephon sound deadening mass is a solvent free deadening

material based on inorganic components with a small addition of organic components with a very high acoustic effectiveness, as

well as insulating properties.

griwephon sound deadening mass is not combustible up to 5.6 mm dry layer thickness according to DIN EN 13501-1 class A2. The deadening material dries quickly up to a thickness of approximately 6 mm, with very good adhesion properties on many different sur-

faces.

#### **Test Certificates**

**General Technical Approval** DIBT, Approval no.: Z-56.4-1025

Fire behavior according DIN EN 13501-1 classification report

Classification of fire behavior A2-s1, d0; MPA Stuttgart, Test certificate No. 903 7215 000-3

#### Physical properties

Colour: beige, other colours on request

Viscosity: thixotrope

Density wet: approx. 1.5 g/cm³
Density dry: approx. 1.3 g/cm³
Solids content (weight %): approx. 80 %
pH-value: approx. 7 – 8.5

Consumption: approx. 1.3 - 1.5 kg per m<sup>2</sup> for 1 mm dry coating

Loss factor: 0.24 according to DIN EN ISO 6721-3

Heat conductivity: approx. 0.2 W/mK



## **Technical Data Sheet**

Last revision: 28.02.2024

# griwephon sound deadening mass

### **Application**

Area of application: griwephon sound deadening mass is used as a deadening effect

on thin-walled sheeting in plant and equipment, vehicle, wagon, shipbuilding and container construction. Further uses for the product include incineration plants, lifts, facades, ventilation ducts,

power stations, etc.

Application: Please pay attention to a uniform layer that is free of gaps. Only

use clean working equipment.

Substrates: Steel plate with corrosion inhibiting primer, galvanized steel plate,

anodized aluminium, coil sheet etc. The surface must be free from

dirt, oil and grease.

Basically, griwephon sound deadening mass AN2-750/EU is suited to be used on coated surfaces, too. Because of the multitude of different surfaces a clean and sustainable coating which is free of

additives on the surface is required.

We principally advise an adhesion test beforehand.

Coating thickness: 5 mm wet coating (corresponds to 4 – 4.5 mm dry coating) possi-

ble in one operation.

Processing equipment: Plunger pumps with a ratio from 8:1 or appropriate screw convey-

ors. For atomization an Airmix gun, 3-5mm nozzle, depending on

application is required. Input pressure: 2.5 -4 bar.

Hand tools like e.g. spatula or mortar trowel are also possible.

Processing temperature: more than 15 °C recommended

Pay attention to humidity at lower temperatures. There must be no

condensation on the substrate.

Coating below 8°C is not possible.

Drying: Transport-dry after 12 to 18 hours with a dry-coating of 5 mm and

a standard climate of 20/55. Forced drying possible up to 50 °C.

When processing outdoors, the weather conditions must allow the

coating to dry completely.

Clean-Up: Immediately in the wet state with water, if necessary in addition

with a household detergent.

### Consignment & Storage

Packaging: 40 kg one-way-hobbock, 250 kg steel drum with inlet

Storage: Keep dry and cool, but frost free! The product can be stored for a

minimum of 9 months when kept sealed in the original container. Once the container is opened or diluted, use it soon and keep it

tightly closed for storage.



## **Technical Data Sheet**

Last revision: 28.02.2024

# griwephon sound deadening mass

Disposal:

Completely emptied containers can be recycled. Containers with hardened remains are residual waste. Containers with liquid remains are special waste and should be disposed at special collecting points according to the locally valid laws on waste disposal. You will find further information regarding the correct disposal on our MSDS

### **Hazardous warning**

No labelling required as product is non-hazardous. Please also follow the instructions on the MSDS.

#### You want advice?

Get in touch with us. We are looking forward to your inquiry.